

TECHNICAL DATA SHEET

Pro Power

0W-20 ECO C5 C6 FD

1 Litre, 5 Litre, 20 Litre & 199 Litre

Product Description

Pro Power Ultra 0W-20 ECO C5 C6 FD is a fully synthetic low SAPS, fuel efficient motor oil suitable for use in both petrol and diesel engines. Designed to give reductions in fuel consumption and excellent protection during cold start up. Recommended for many modern vehicles, including those from Ford, Vauxhall/Opel, Mercedes-Benz, Jaguar Land Rover, Hyundai, Kia, Toyota and others.

Recommended for use by Pro Power for the following manufacturer's specifications

ACEA: C5 & C6

API: SN Plus, SP & SP RC

Ford: WSS-M2C947-B1, WSS-M2C952-A1 & WSS-

M2C962-A1

EXPERTS IN HIGH QUALITY OIL

MB: 229.71 & 229.72 STJLR: .03.5006 Opel: OV0401547-A20

GM: Dexos™ D



* Image for illustrative purposes only

Size	Part No	Barcode
1 Litre	A375-001	5020618210634
5 Litre	A375-005	5020618210641
20 Litre	A375-020	5020618210658
199 Litre	A375-199	5020618210665

Product Benefits

- * Latest synthetic technology motor oil
- * Provides Low Speed Pre-Ignition (LSPI) protection
- * Provides significant reductions in fuel consumption
- * Exceptional low temperature characteristics meaning that the oil circulates quickly even in the most demanding cold start conditions

Product Usage

Use as per engine manufacturers recommendations.

Storage Instructions

Store sealed and upright in a cool dry place & out of the reach of children.

Revision: 2 | Date: 20/01/2025



TECHNICAL DATA SHEET

Pro Power

0W-20 ECO C5 C6 FD

1 Litre, 5 Litre, 20 Litre & 199 Litre

Shelf Life

EXPERTS IN HIGH QUALITY OIL

5 Years from date of manufacture.

Appearance : Amber liquid

Odour : Characteristic

Solubility : Insoluble in water

Percentage of Biodiesel : Nil

Test	Method	Unit	Min.	Max.	Typical
Viscosity, Kinematic 100°c	ASTM D445	mm²/s	7.8	<9.3	8.52
Viscosity, CCS	ASTM D4684	mPa.s		<6200	5812
Total Base Number	ASTM D2896	mg KOH/g	8		
Pour Point	ASTM D97	°c		-48	
HTHS Viscosity	ASTM D4683	mPa.s	2.8	<2.9	
NOACK Volatility	ASTM D5800	%		11	
Viscosity, Kinematic 40°c	ASTM D445	mm²/s			45.452
Density	ASTM D792	@ 15°c			0.845

Safety Precautions

Please see our latest EC Safety Data Sheets for details.

Transport Classification

Please see our latest EC Safety Data Sheets for details.

Revision: 2 | Date: 20/01/2025